



ARDEX X 17 WHITE

Flexible Non Slump Wall & Floor Tile Adhesive

Superior flexibility – achieves S1 classification

Non slump – ideal for large format and heavy tiles

Ideal for all tile types including fully vitrified, porcelain and mosaics



ARDEX Australia Pty Ltd
2 Buda Way
Kemps Creek NSW 2178
Phone: 1300 788 780
Email: technicalservices@ardexaustralia.com
ardexaustralia.com

ARDEX New Zealand Ltd
15 Alfred Street, Onehunga Auckland,
New Zealand 1061
Phone: 0800 227 339
Email: info@ardexnz.com
ardex.co.nz

ARDEX X17 WHITE

Flexible Non Slump Wall and Floor Tile Adhesive

DESCRIPTION

ARDEX X17 White is a polymer fortified cement-based wall and floor tile adhesive that has been specially formulated with mastic type properties. ARDEX X17 White has an extended open time, is non slump and flexible. Mix with water to achieve a mortar suitable for internal and external use in residential and light commercial applications. ARDEX X17 White meets the Green Building Council of Australia Green Star requirements for Ceramic Tile Adhesives.

TO (SUBSTRATES)

- Concrete, renders, screeds
- Fibre-cement sheet, plasterboard on walls
- Compressed fibre-cement sheet on floors
- ARDEX liquid applied undertile waterproofing membranes
- Existing ceramic tiles (internal dry areas)
- Ceramic Tile Underlay (CTU)

FOR FIXING (TILE TYPES)

Fully vitrified and ceramic tiles, porcelain, natural stones (excluding moisture sensitive) and mosaics.

SUBSTRATE PREPARATION

The surface being adhered to must be clean, firm and free of dust, dirt, oil, grease, curing compounds, release agents and other barrier materials, as well as being strong enough to support the weight of the tiles being fixed. Ensure surfaces are dry before tiling, with no residue or permanent damp.

Ensure that the substrate's required drying time, as given in the relevant part of AS 3958, is allowed to elapse prior to fixing the tiles. Prime porous substrates with ARDEX Multiprime.

CONCRETE

This includes precast, in-situ and wood floated concrete. As concrete exhibits drying shrinkage, allow to cure for at least 4 weeks prior to tiling. Any surface laitance, concrete sealers, curing compounds, and other materials should be removed from the surface prior to tiling. Steel trowel finished concrete shall be roughened mechanically to remove laitance and provide a good key for tiling.

The surface shall be true and level and pitched to drains where required. The concrete should have adequate surface profile (e.g. CSP 2-3) to provide a mechanical key. Smooth surfaces and/or dense concrete greater than 35MPa must be mechanically prepared prior to tiling.

CEMENT RENDER / SCREEDS

New renders and screeds should be finished with a wood float to the required surface regularity. Screeds shall be pitched to drains where required. For bonded screeds allow 24 hours to cure prior to tiling. For unbonded screeds allow at least 7 days to cure prior to tiling.

PLASTERBOARD/MEDIUM DENSITY FIBRE-CEMENT SHEET (WALLS)

Tiles can be fixed directly provided these boards are firmly and rigidly fixed in accordance with manufacturer's instructions to adequately support the tile bed. Priming is recommended for fibre-cement sheet but is not usually necessary for plasterboard except when jointing compound is used.

COMPRESSED FIBRE-CEMENT SHEET (FLOORS)

These sheets must be fixed strictly in accordance with manufacturer's instructions and be deemed suitable for the application by the manufacturer.

EXTERNAL FIBRE CEMENT SHEET

Tiling over compressed fibre-cement sheet for external flooring applications should be carried out as per sheet manufacturer's recommendations and Australian Standard AS 3958.

ARDEX LIQUID APPLIED UNDERTILE WATERPROOFING MEMBRANES

ARDEX undertile waterproofing must be applied according to instructions and thoroughly dry prior to tiling.

EXISTING CERAMIC TILES (INTERNAL DRY AREAS ONLY)

These include sound, clean, glazed and unglazed tiles. Existing tiles must be firm and stable. Roughen the surface by mechanical means, clean off contamination and dust before tiling. Ensure that at least 80% of the glaze is removed. Prime with ARDEX Multiprime or ARDEX P9.

CERAMIC TILE UNDERLAY (CTU)

Should be fixed as per the manufacturer's instructions. The CTU must be a minimum of 6mm and made specifically for this purpose. Tiles under 100mm edge length cannot be fixed using this method. CTU can be applied to plywood and particleboard but not strip timber. Please refer to ARDEX Technical Services for further details.

MIXING

ARDEX X17 White powder is added to clean water in a clean container. The most efficient method of mixing is by using a mixing paddle and a heavy duty electric drill (650rpm), and mixed thoroughly to give a lump free easily worked mortar of a thick creamy consistency. Mix for at least 2 minutes allow to stand for 5 minutes, and mix a second time for 2 minutes.

A 20kg bag of ARDEX X17 White requires approximately 6 - 6.5 litres of water. Do not add additional water.

The consistency of the adhesive can be slightly adjusted to suit site conditions and size, weight and type of tiles to be fixed. Do not apply at temperatures below 10°C. The pot life of the mixed mortar is approximately 3 hours at 23°C and 50% relative humidity.

ARDEX X17 WHITE

Flexible Non Slump Wall and Floor Tile Adhesive

FIXING TECHNIQUE

Before fixing ensure the substrate has been prepared and the tiles are free from dust. Tiles should be fixed in accordance with Australian Standard AS 3958.

Substrate surface, type and size of the tiles will determine the selection of the trowel. Refer to AS 3958 for the trowel size guidance depending on nominal tile size.

The tiles must be pressed firmly into the freshly combed mortar bed to ensure good contact with the mortar. Slide the tile at right angles to the notch pattern to ensure 100% coverage on the back of the tile. Tiles with ribbed or keyed back profiles should also be buttered to ensure complete coverage. Lift a tile from time to time to check that there are no voids beneath the tile. Do not spot fix. Any surplus adhesive must be removed from the surface of the tile and joints, before the adhesive sets.

ARDEX X17 White has an open time of 30 minutes and an adjustment time of 20 minutes. ARDEX X17 can be applied at a bed thickness greater than 3mm or less than 10mm.

Please be aware of site conditions when considering these times and only spread enough adhesive so that the tiles can be fixed while the mortar is still wet. All tools should be cleaned with water immediately after use.

MOVEMENT JOINTS

Movement joints must be in accordance with Australian Standard AS 3958.

GROUTING

Grouting can proceed once the tile bed has hardened sufficiently so that tiles will not be dislodged. Grouting and traffic may be allowed after approximately 24 hours at 23°C and 50% relative humidity. Allow longer for dense tiles/substrates, humid climates and low temperatures.

The tile joints should be grouted with the appropriate ARDEX grout.

COVERAGE

A 20kg bag of ARDEX X17 White is sufficient for approximately 10m² on walls, using a 6 x 6 x 6mm notched trowel and 6m² on floors using a 10 x 10 x 10mm notched trowel. The coverage will vary depending on substrate condition, tile type and application technique.

PACKAGING

ARDEX X17 White is packed in polylined paper sacks – net weight 20kg. Dispose of packaging and recycle where possible.

SHELF LIFE

ARDEX X17 White has a shelf life of 12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

Pay attention to the following

- Do not use ARDEX X17 White in continuous immersion applications e.g. swimming pools, tanks, etc. ARDEX provides other systems.
- Do not use over metal or similar surfaces.
- ARDEX X17 White should not be used on floors with a deflection greater than the joist span divided by 500. Joist span must comply with AS 1684.
- ARDEX X17 White should not be used over substrates subject to shrinkage and other movement e.g. timber, ARDEX provides other systems.
- For setting of moisture sensitive natural stones, please refer to products in the ARDEX Natural Stone System.
- Dimensional instability in natural stone ranges is often difficult to detect visually and may require thermal and moisture stability testing to ensure that adhesive recommendations can be warranted. Contact your tile supplier for further information or ARDEX Technical Services for information and testing.

TECHNICAL PROPERTIES

Colour	White
Mixing Ratio	1 vol water: 3 vol powder, approximately 6 - 6.5 litres water per 20kg powder

APPLICATION PROPERTIES AT 23°C AND 50% RH

Open Time	30 mins
Adjustment Time	20 mins
Grouting Time	24 hours
Pot Life	3 hours
Sagging	None
Underfloor Heating	Yes

MECHANICAL PROPERTIES (ISO 13007) Tensile Adhesion Strength after

28 Days Dry	≥1.0 MPa
Water Immersion	≥1.0 MPa
Heat	≥1.0 MPa
Freeze Thaw	≥1.0 MPa
Classification	C2 TE S1

ARDEX X17 WHITE

Flexible Non Slump Wall and Floor Tile Adhesive

SAFETY DATA

Wear protective gloves, protective clothing, eye protection and face protection. Do not breathe dust/fumes. Wash all exposed external body areas thoroughly after handling. Contaminated work clothing should not be allowed out of the workplace.

IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing. Immediately call a doctor. IF ON SKIN: Wash with plenty of water and soap. If skin irritation or rash occurs: Get medical advice / attention. Take off contaminated clothing and wash it before reuse. IF INHALED: remove person to fresh air and keep comfortable for breathing. Store locked up. Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation. Additional information is in the Safety Data Sheet (SDS) at ardexaustralia.com

This product causes skin irritation. May cause an allergic skin reaction. Causes serious eye damage. May cause respiratory irritation. Suspected of causing genetic defects. May cause cancer. Causes damage to organs through prolonged or repeated exposure.

GUARANTEE

ARDEX Australia Pty Ltd (“we” or “us”) guarantees this product (“our goods”) is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (ARDEX Australia Pty Ltd, 10 Giba Drive Kempers Creek NSW 2178; Toll Free: 1800 224 070; Email: technicalservices@ardexaustralia.com) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a “consumer” under the Australian Consumer Law and to that extent you need to be aware that: “Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss of damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure”.

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. Users are advised to confirm that this product is suitable for their application and conforms with the specifications of the system. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2025.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

This data sheet was issued in June 2025 and is valid for 3 years, in some instances a newer version may be published. Always refer to ardexaustralia.com for the latest technical data from ARDEX Australia Pty Ltd.