



Hypersil 911

100% Neutral Cure Silicone Sealant

Features

- ▶ Neutral Cure
- ▶ 100% Silicone
- ▶ UV Stable
- ▶ General Glazing Applications
- ▶ Flexible $\pm 25\%$
- ▶ VOC: 31gr/L
- ▶ Long Term Durability
- ▶ Easy to Apply
- ▶ Available in Colours

Product Description

Pasco **Hypersil 911** is a high performance neutral cure silicone sealant which cures to form a tough and flexible waterproof seal. Formulated for a wide range of glazing, weatherproofing and specialist trade applications.

Features & Benefits

- Neutral cure
- Highly flexible $\pm 25\%$
- Excellent weathering
- Long term durability
- Will not corrode metals
- Superior adhesion
- VOC: 31gr/L
- Exceptional adhesion
- 100% Silicone
- Low odour
- Non-slumping
- Easy to apply
- Easy to tool
- Available in colours
- UV Stable
- Extensive colour range

Uses

- General purpose glazing
- Curtain walls
- Construction joints
- Building claddings
- Perimeter sealing of door and window frames

Provides excellent adhesion to:

- Glass
- Aluminium
- Steel
- Concrete
- Stainless steel
- Ceramic tiles
- Painted and powder coated surfaces*
- Natural and reconstituted stone*
- Most plastics*

**Test surface area for compatibility (adhesion/staining) prior to application.*

Application Instructions

Substrate Preparation

All surfaces must be clean, dry, sound and free from dust, oil, rust, old sealant or any other contamination.

Glass and metal should be cleaned with methylated spirits. Solvent should be wiped from the surface with a clean dry cloth.



Hypersil 911

100% Neutral Cure Silicone Sealant

Joint Design

Open cell polyethylene backing rod shall be used to control the depth of the joint sealant application to the recommended thickness. Correct joint design is necessary to ensure sealants do not split or tear.

The size of the closed cell backing rod used shall allow for 25% compression when inserted into the joint.

Joint Width	Joint Depth
6mm to 10mm	Equal to joint width
10mm to 20mm	10mm
20mm to 25mm	Half of joint width

Coverage

Meters per 300ml cartridge (approx.)

Joint Depth	Joint Width (mm)							
	6	8	10	12	15	20	25	
6mm	8.3	6.3	5	4.1	3.3	2.5	2	
8mm	-	4.6	3.7	3.1	2.5	1.8	1.5	
10mm	-	-	3	2.5	2	1.5	1.2	
12mm	-	-	-	2.1	1.6	1.2	1	

Application

Hypersil 911 sealant shall be installed using conventional caulking tools, materials and methods.

1. Cut tip off cartridge.
2. Cut nozzle to the desired bead size at 45° angle.
3. Apply sealant into joint ensuring wetting of both sides.
4. Dry tool sealant immediately to a smooth finish.
5. Remove excess sealant immediately with cloth and solvent (eg. mineral turpentine).

Precautions

- Not to be used as a structural glazing sealant.
- Not paintable.
- Not suitable for certain rubber products where bleeding of plasticiser may occur.
- Not to be used for aquariums.
- Not to be used for polycarbonate plastic sheeting
- Not to be used for joints subjected to permanent water immersion.
- Not to be applied on any substrate containing bitumen.
- Do not use as a trafficable sealant.

Packaging

Hypersil 911 is available in 300ml cartridges, 20 cartridges per carton.

Colour

Hypersil 911 is available in Translucent, White, Chocolate, Bronze, Grey, Silver, Charcoal, Volcano & Black.

Shelf Life

12 months minimum, when stored in cool dry conditions below 28°C.



241 Ingles Street
Port Melbourne, VIC 3207
Ph: (03) 9429 9111

4/14 Tennyson Road
Gladesville, NSW 2111
Ph: (02) 9817 4441



Hypersil 911

100% Neutral Cure Silicone Sealant

Health and Safety

Keep out of reach of children. This product emits Methyl Ethyl Ketoxime (MEKO) whilst curing. Wear suitable protective clothing, gloves and eye/face protection. Uncured sealant may cause skin, eye and respiratory system irritation. Use only in well ventilated areas.

In case of contact with eyes, rinse immediately with plenty of water and contact a Doctor or Poisons Information Centre (**Ph 13 11 26**). In case of skin contact, wash affected area with hand cleaner followed by soap and water.

Material Safety Data Sheets must be read and understood prior to using **Hypersil 911**.

Hypersil 911 Technical Specifications		
Property	Test Method	Result
Elongation		400%
Hardness (Shore A)	ASTM D2240	30
Joint Movement		± 25%
Sag/Slump		Non slump (0.1")
Tensile Strength KHF/CM2 (MPA)		20 (2.0)
Cure Method		Neutral
Specific Gravity		1.04
Skin Time @ 20°C & 50% RH		8-10 min
Cure Time 10mm @ 25°C		5-7 Days
Operating temperature range		-62°C to +170°C

Pasco Construction Solutions Pty Ltd offers its' products for sale, subject to its standard terms and conditions of sale, which are available upon request. All endeavors have been made to ensure the information provided in this technical data sheet is accurate and correct, however as the use of this material is beyond the supplier's control, liability is limited to replacement of material proven faulty. It is the responsibility of the purchaser to ensure that the product is suitable for the specific application and that it is applied in accordance with the supplier's recommendations.



**241 Ingles Street
Port Melbourne, VIC 3207
Ph: (03) 9429 9111**

**4/14 Tennyson Road
Gladesville, NSW 2111
Ph: (02) 9817 4441**